

**Product Name**

TP-4006 Polyurethane



High Impact + High Heat Resistant

Description

TP-4006 is a tough, impact resistant polyurea formulated for room temperature hand-batch systems or vacuum-assisted casting methods. Excellent physical properties can be obtained without the utilization of mercury, MOCA, or TDI.

Physical Properties

Mix Ratio	Resin:Hardener (parts by weight)		100:65
Mix Ratio	Resin:Hardener (parts by volume)		100:63
Viscosity (cps@100°F)	Resin	1600	Gel Time
	Hardener	500	10 ± 2 Minutes
	Mixed	400	Demold Time*
			1 Hour at 150 °F
			Color
			Translucent Amber
Specific Gravity (g/cc)	Resin	1.2	* Demold time is always mass dependant.
	Hardener	1.24	

Cure 1 ► 1 hour at 150 °F + 24 hours at 77 °F
 Cure 2 ► 1 hour at 150 °F + 7 days at 77 °F

Cured Properties

	Method	Cure 1	Cure 2
Hardness (shore D)	ASTM D-2240	80 ± 5	80 ± 5
Tensile Strength (psi)	ASTM D-638	9,500	11,400
Elongation at Break	ASTM D-638	11%	7%
Compression Strength (psi)	ASTM D-695	N/A	N/A
Compression Modulus (psi)	ASTM D-695	N/A	N/A
Ultimate Flex Strength (psi)	ASTM D-790	8,500	13,500
Flexural Modulus (psi)	ASTM D-790	185,000	300,000
Notched Izod (ft.lbs./in.)	ASTM D-256	1.8	1.5
Linear Shrink (in./in.)	ASTM D-2566	0.002-0.005	0.002-0.005
Heat Deflection Temp. (66psi)	ASTM D-648	N/A	N/A
Heat Deflection Temp. (264psi)	ASTM D-648	130°C / 266°F	140°C / 285°F
Specific Gravity (g/cc)		1.21	1.21

Processing Notes

Formulated for hand-batch equipment. For best results, de-air the material prior to casting, then pressurize to 60 psi until cured. The hardener component will darken as it ages. It is recommended that dry nitrogen be used to protect the material from oxidizing and being moisture contaminated.

Agitate the hardener and resin before use to ensure that the formula is homogeneous.

Safety and Handling

DO NOT USE UNTIL MSDS HAVE BEEN READ AND UNDERSTOOD. Store containers in a dry location. Partially used containers should be blanketed with dry nitrogen to prevent moisture contamination. Moisture will react with the resin component, creating carbon dioxide gas and a possible pressure increase in the container.
 SPECIFICATION WRITERS: The above values are meant to represent typical properties only. Users are encouraged to qualify products in their own laboratories prior to specification publication.
 PURCHASER has the responsibility for determining any applicability of and compliance with federal, state, and local laws concerning labeling, use, and waste disposal, particularly in making consumer items. Innovative Polymers, Inc. makes no warranty, expressed or implied, for merchantability or fitness of use. The sole liability of Innovative Polymers, Inc. for any claim arising out of the manufacture, use, or sale of its products shall be the buyers purchase price.